

PRODUCT DATA SHEET

BAGGES CGF-S-1

Weave : Cross twill

Properties				
	DESCRIPTION	TEST METHOD	VALUES	UNIT
BASE FABRIC				
Yarn Warp Weft	DIN 53830-3 EC9 EC0		136 ±5% 136 ±5%	
Thread count Warp ends Weft ends	EN 1049-2		17,0 ±5% 13,0 ±5%	1/cm 1/cm
Weight	DIN 12127	420		g/m ²
Weave	ISO 9354			
Temperatur resistance		550 continous		°C
COATED FABRIC				
Coating	Coated with high temperature flame retardant silver grey silicone rubber on one side.			
Weight	DIN EN 12127	510 ±10%		g/m ²
Thickness	DIN EN ISO 5084	0,45 ±10%		mm
Tensile strength Warp Weft	DIN EN ISO 13934-1	>3.900 >2.600		N/5 cm N/5 cm
Temperatur resistance		250		°C

NB: Unless otherwise stated, all values quoted are nominal measurements. The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.