

PRODUCT DATA SHEET

BAGGES CAF-A-1

Description	Aramid fabric aluminised on one side with highly reflective film.
Colour	Inner surface yellow, outer surface reflective aluminium
Weave of base fabric	3/1 Herringbone Twill
Finish	Aluminised on outer surface with metallised PET film
Weight (g/m²)	530
Thickness (mm)	0,80
Flammability test to EN532:1994 10 sec flame applied to face of vertical sample	Negative reaction to flame - PASS
Tensile Strength (In-house test)	Warp: 2940 N/50mm (Mean) Weft: 1366 N/50mm (Mean)
Thermal test to EN407:1994	<u>Performance Level</u>
Contact Heat EN702	Level 1
Convective Heat EN367	Level 2
Radiant Heat EN366	Level 4
<u>Molten Metal Splash</u>	
Splashes EN348 Small	Level 4
Quantities EN373 Large	Level 3
Resistance EN388 Abrasion	Level 1
Resistance EN388 Tear	Level 4
Indicative test to MIL-C-87076A	
Wet flexibility (Part 4.5.31/)	No evidence of cracking or delamination
After wet flexing (Part 4.5.51/)	No evidence of delamination
Fabric care	Wipe clean - do not launder Keep the fabric as dry as possible. If garments become wet with perspiration, hang to dry thoroughly before re-use.
Roll dimensions	50 metre length x 1 metre width
All figures quoted are nominal	
The information contained in this data sheet is believed to be true at the time of printing. Any statements contained or inferred to within are an expression of opinion and presented without guarantee. It is up to the user to determine suitability of use, or potential patent infringement for specific applications.	