

VIDAFLEX SD350

Composition

VIDAFLEX SD350: Silicone elastomer coated knitted "E"- glass insulating sleeving.

VIDAFLEX SD350 insulating sleeveings offer a high degree of flexibility and they provide a good resistance against ozone, ultraviolet radiation and humidity.

VIDAFLEX SD350 insulating sleeveings are compliant to the requirements of the directive 2002/95/EC (RoHS).

Max. short term temperature: 250°C.

Application

Protection and insulation of leads and wiring harness in household appliances, lamps and vehicles.

Insulation of the internal wiring of all types electrical machines.

Thermal Class 180 (Class H) according to IEC 60085

Bore size (mm)	Nom. wall thickness (mm)	Weight approx. (g/m)	Breakthrough voltage at 20°C (kV)
1,0 ± 0,20	0,80	10	≥ 7,0
2,0 ± 0,20	0,80	11	≥ 7,0
3,0 ± 0,20	0,80	13	≥ 7,0
4,0 ± 0,25	0,80	17	≥ 7,0
5,0 ± 0,25	0,80	19	≥ 7,0
6,0 ± 0,25	0,80	22	≥ 7,0
7,0 ± 0,25	0,80	26	≥ 7,0
8,0 ± 0,25	0,80	29	≥ 7,0
9,0 ± 0,50	0,80	32	≥ 7,0
10,0 ± 0,50	0,80	36	≥ 7,0
12,0 ± 0,50	1,00	45	≥ 7,0
14,0 ± 1,00	1,00	55	≥ 7,0
16,0 ± 1,00	1,00	64	≥ 7,0
18,0 ± 1,00	1,00	75	≥ 7,0
20,0 ± 1,00	1,00	88	≥ 7,0
22,0 ± 1,00	1,00	92	≥ 7,0
24,0 ± 1,00	1,00	117	≥ 7,0
25,0 ± 1,00	1,00	124	≥ 7,0
Measurement according to EN 60684-2			
Availability			
Standard length	250, 100, 50 and 25 m spools, dependant on bore size. Cut to length on request.		
Colour	Black		

All values stated are to be seen as typical values. We reserve the right to introduce changes within the framework of further technical development. We do not accept any obligations or liabilities in respect of this information. Status: 01/2009
 KREMPEL GmbH · Papierfabrikstrasse 4 · D-71665 Vaihingen / Enz · Tel. +49 (0) 7042 915-0 · E-mail: info@krempel-group.com